
PARKER PolyPak SEALS



GENERAL The Parker PolyPak is a patented precision molded multi-purpose seal. The Parker PolyPak combines an O-ring type synthetic rubber O-Spring with a conventional lip-type seal (see Figure 1.) to produce a unique sealing device capable of sealing both vacuum, high and low pressure.





FIGURE 1

POLYPAK THEORY Conventional lip seals, such as the standard U-Packing are prone to leakage under low pressure because little or no LIP LOADING is inherent in the basic seal desian.

The Parker PolyPak however, is a squeeze type seal and provides high sealability at low pressure. As system pressure increases, additional force is applied to the PolyPak's seal interface and as pressure continues to increase, lip loading is automatically increased to compensate for this higher pressure and thus maintain a positive, leak-free seal from hard vacuum to over 60,000 psi with proper design and auxiliary devices (see Figure 2.).



SYSTEM PRESSURE

FIGURE 2

O-SPRING IS SQUEEZED CREATING A POSITIVE UNIT **POLYPAK** ON INDEPENDENT OF SYSTEM PRESSURE POLYPAK THUS SEALS EFFECTIVELY AT LOW PRESSURE OR VACUUM.

LIPS ARE FORCED AGAINST SURFACES TO BE SEALED AS A FUNCTION OF APPLIED SYSTEM PRESSURE PLUS THE INITIAL O-SPRING SQUEEZE. O-SPRING PRESSURE REMAINS CONSTANT FROM ZERO PRESSURE TO INFINITY.

POLYPAK ADVANTAGES In addition to providing superior sealing in vacuum, low and high pressure applications, the PolyPak offers a number of distinct advantages over conventional symmetrical or non-symmetrical U-Packings.

- (1) The PolyPak's O-Spring stabilizes the seal under extreme pressures preventing seal lip distortion and rolling or twisting in the gland.
- ľow or temperature extremes, the O-Spring maintains lip loading on both I.D. and O.D. of the seal interface.
- (3) The PolyPak seal can be stretched or squeezed to accomodate oversize cylinder bores and undersize rods. As long ·HIGH CONFORMABILITY as the seal CROsS-SECTION is correct in .EXCELLENT SEALABILITY relation to the radial groove dimensions, the PolyPak will compensate and maintain proper lip loading.
- The range of materials .HIGH STABILITY available to the user of the Parker PolyPak insures .CHOICE OF STYLES the proper combination or abrasion, extrusion, temperature resitance and fluid compatibility which .EASILY RETROFITS produces high sealability and long seal life.



·HIGH MEMORY OF O-SPRING

·LONG SERVICE LIFE

·CHOICE OF MATERIALS

OTHER SEALS

PARKER POLYPAK STYLES

STANDARD

Standard PolyPak seals are square in crosssection and are suitable for a wide variety of rod and piston applications. Available in crosssections from 1/8" to 1" and diameters to 90", the Standard PolyPak is ideal for retrofit of existing seal grooves.



Deep PolyPak seals are rectangular versions of the Standard PolyPak. The added length improves stability in high-shock, heavy duty applications. Available in cross-sections from $1\dot{/}8$ " to 1" and diameters to 90".



TYPE "B"

Type "B" PolyPak seals add a back-bevel lip to the Deep PolyPak shape and thus align the seal interface near the centerline of the O-Spring to provide increased squeeze (and sealability). This highly stable configuration provides excellent low pressure sealing as well as "super-pressure" capability. Available in all sizes from 1/8" to over 90" diameter.





www.sealsonline.com

Vanier (QC) St-Laurent (QC)

Tel.: (418) 688-3202 Fax.: (418) 688-4272 Tel.: (514) 334-2220 Fax.: (514) 333-8329 Mississauga (ON) Tel.: (905) 238-5885 Fax.: (905) 281-0763



PolyPak DESIGN DATA

INTRODUCTION This section covers the basics of PolyPak Seal design and is intended to give the designer / engineer a brief overview of the requirements for reliable seal performance. **Complete design and engineering assistance is available by calling us during normal business hours.**

ROD SEALING WITH POLYPAK As a general rule, rod seals are more critical in nature than their companion piston seals. As most equipment manufacturers require "dry rod" capability, both to conserve system fluid and to avoid leakage for cosmetic and environmental reasons, the design and selection of the rod seal can be rather more difficult than it's piston counterpart.

Parker recommends the use of the Type B PolyPak for rod seal applications. First, because of the excellent film-breaking capability of the back-beveled design. Second, the higher level of lip loading provided by the Type B offers maximum sealability and finally because the long body of the design provides maximum stability and extrusion resistance.

PISTON SEALING WITH POLYPAK Piston Seals can be classed in two categories, SINGLE ACTING and DOUBLE ACTING. The single acting seal is only required to seal in a single direction as system pressure is seen on only one side of the cylinder (return of the piston in a single acting system is accomplished either by gravity or spring loading). The double acting cylinder requires that the piston be sealed in both directions of stroke as system fluid is applied to one side or the other to achieve movement.

Parker recommends the use of either (1) two Standard (2) two Deep PolyPak or (3) one Type B PolyPak with PIP ring (see PIP SEAL) on double acting cylinders. **DO NOT USE TWO TYPE B POLYPAKS in double acting applications** as the extreme sealing ability of the Type B PolyPak is such that a PRESSURE TRAP (see pressure trap, page 6) may be created.

PISTON & ROD SEAL DESIGN HINTS Some other things to remember when considering piston & rod seal design are:


- Surface Finish-An 10-16 rms finish is preferred on all dynamic surfaces and a 10-32 rms finish for static (see SURFACE FINISH on page 6).
- SURFACE FINISH on page 6).

 (2) Adequate Bearing surface Be sure to allow for sufficient bearing surface to protect against side loading.
- (3) Wear Bands Use of wear bands can cause unexpected problems with rod & piston seal geometry. Consult factory for assistance.
- (4) Seal cross-section Use the largest seal cross-section that your design and good installation practice will allow. Parker PolyPaks are available in a number of C / S dimensions to suit your requirements.

SUGGESTED CROSS-SECTIONS : Up to 2" Dia. -3/16 in. 5" to 10" -3/8" 2" to 5" Dia. $-\frac{1}{4}$ in. Above 10" $-\frac{1}{2}$ in.

(5) Installation – Break all sharp edges on metal components to prevent damage to seal lip during assembly and use adequate lubrication. See Chamfer Data, page 6). **SYSTEM PRESSURE** The ability of seal materials to withstand the pressure of hydraulic system fluids varies with the compound. The chart below lists the MAXIMUM recommended operating pressure to which the material may be exposed without special back-up devices or reduced clearances with minimum risk of extrusion.

MAXIMUM RECOMMENDED PRESSURE FOR PARKER PACKING COMPOUNDS*



*TEST CONDITIONS

- 1. 100.000 PRESSURE CYCLES AT RATE OF 60 PER MINUTE FROM ZERO TO INDICATED PRESSURE.
- 2. TEST TEMPERATURE +160°F.
- 3. TESTS CONDUCTED WITH NO BACK-UP DEVICES.
- MAXIMUM .010 DIAMETRICAL & .005 RADIAL CLEARANCE.

ENGINEERED DESIGN CHARTS There are complete design tables available for all PolyPak Seals. We have included sufficient information at the end of this catalog to allow the designer or user to select the PolyPak needed for his application. Both Piston and Rod design information are shown.







MATERIAL SELECTION

INTRODUCTION This section briefly covers the wide range of basic seal materials available to the user of the Parker TOTAL Sealing System.

MATERIAL COLOR CODE Following each material type there is a color description indicating the base color of the polymer for identification purposes.

WHY DIFFERENT MATERIALS? New hydraulic fluids are being introduced into service at a rapid rate and system operating parameters (Pressure & Temperature) are changing to meet user needs. To keep pace with these changing conditions. Parker is constantly testing and developing new seal materials to extend service life. The material types listed below are general categories only. For complete technical information, ask Parker for test reports covering your specific fluid or application.

MOLYTHANE • GRAY

Parker Molythane is the oldest and most generally specified seal material for hydraulic service. This unique material is a blend of Polyurethane and MolyDiSulfide (for reduced friction) developed for long service in all petroleum-based fluids. The Temperature Range of Molythane is -65°F to +200°F (-54°C to +93°C), 140°F in water and high water based fluids. Parker's Molythane offers excellent resistance to extrusion and abrasion. The most popular compound is P4615A90.

DYNOTHANE • CLEAR

Parker Dynothane is a polyurethane material with improved physical properties. Dynothane offers improved compression set resistance, higher rebound resilience and tensile strength resulting in improved seal performance. Fluid compatibility same as Molythane. Temperature range is -65°F to +200°F (- 54° C to $+107^{\circ}$ C). The Dynothane compound number is P4693A90.

ULTRATHANE K-24 • YELLOW

Ultrathane is a new polyurethane material from Parker offering up to 43% reduced friction over conventional urethane materials. Because of this reduced friction and the resulting lowering of frictional heat build-up at the seal interface, the operating temperature of this material is -65°F to ± 225 °F (-54°C to ± 107 °C). Ultrathane fluid compatibility is the sane as Parker's other high tensile urethane materials and is good for service to 5000 psi at recommended dimensions and tolerances. The Ultrathane compound number is P4622A90.

NITROXILE ● BLACK

Nitroxile is a Carboxylated Nitrile material offering 3 to 5 times greater resistance to abrasion than conventional nitrile compounds. This material is also available with internal lubrication to reduce friction. Nitroxile is suitable for general hydraulic service in petroleum-based fluids, water-oil emulsions, water-glycol fluids and water base fluids (HWBF). Nitroxile's temperature range is -40°F to +250°F (-40°C to +121°C). The most popular of the Nitroxile materials are N4257A80 (w / internal lubrication), N4274A85 (ELF) for extreme low friction requirements.

POLYMYTE ORANGE

Parker PolyMyte is an "elastoplastic" material with exceptionally high tear strength and abrasion resistance. PolyMyte's high modulus and high durometer (53 & 65 Shore D) make it very suitable for high-pressure service where extrusion is a problem. PolyMyte is suitable for service in petroleum based fluids, water base fluids (HWBF)*, phosphate ester fluids, some chlorinated fluids and solvents. Temperature range is is -65°F to +275°F (-54°C to +135°C), 180°F in water based fluids. The standard compound is Z4651D53. * (under 180°F)

FLUOROMYTE • PURPLE

FluoroMyte was developed to meet seal needs in high-pressure hydraulic systems. FluoroMyte has exceptionally high tear strength and abrasion resistance. It also has lower friction than PolyMyte due to special lubricants disbursed in the base material. FluoroMyte has excellent resistance to oxygen, ozone, petroleum and phosphate ester based fluids. The temperature range of this material is -65° F to $+300^{\circ}$ F (-54° C to $+149^{\circ}$ C). The FluoroMyte compound number is Z4653D58.

FLUOROCARBON ● **BLACK**

Fluorocarbon materials offer the user a wide range of fluid compatibility and broad temperature range often resulting in reduced seal inventory requirements. Fluorocarbon is suitable for use in most hydraulic fluids (except Skydrol types and some ester / ether fluids). Temperature range is -20°F to +400°F (-29°C to +204°C). The standard Fluorocarbon compounds are V4208A90 and V42266A95 (+450°F).

NITRILE ● BLACK

Nitrile is one of the oldest and most popular seal compounds. Nitrile compounds have good resistance to abrasion, extrusion and compression-set and are generally suitable for service in petroleum, water-oil emulsions and water-glycol fluids. The temperature range of Nitrile is -40°F to +250°F (-40°C to +121°C). Special Nitrile materials may have a higher upper limit (to' +300°F). The general usage Nitrile compound is N4121A90 for PolyPak seals.

ETHYLENE PROPYLENE ● BLACK

Ethylene Propylene or EPR is a useful seal material for sealing phosphate ester type hydraulic fluids such as Skydrol. Ethylene Propylene is also suitable for use with automotive brake fluids, weak caustics, acids and Methyl Ethyl Keytone. This material SHOULD NEVER BE EXPOSED TO ANY TYPE PETROLEUM BASE FLUID OR LUBRICANT. Ethylene Propylene has a temperature range of -65°F to +300°F (-54°C to +149°C) and to +400°F in steam. The standard EPR compounds are E4207A90 and E4183A80. E4207A90 is a newly developed geothermal EPR material for service to 600°F in steam applications. Also has good explosive decompression resistance in CO₂.

PARKERTHANE OWHITE

Vanier (QC)

St-Laurent (QC)

Parkerthane is an improved formulation of polyurethane materials with extreme resistance to extrusion and abrasion. Parkerthane is suitable for use in most petroleum-based fluids. The temperature range of Parkerthane is -65°F to +200°F (-54°C to +93°C). Parkerthane is identified by compound number P4611A90.



Solution S

MATERIAL SELECTION (con't)

TEMPERATURE COMPATIBILITY is one of the prime considerations involved in seal material selection. In selecting a seal material, the user must determine both the upper and lower EXTREMES at which the seal will be expected to function and also take into account the TIME (duration) to which these extremes of temperature excursion will be experienced, bearing in mind that compression set (and therefore sealability) is a function of the time / temperature relationship. The general temperature capabilities for Parkers hydraulic and pneumatic seal materials are shown in the chart at right.

PRESSURE COMPATIBILITY is another consideration when selecting a seal material. This characteristic is determined by the durometer (hardness) of the material and by its internal chemistry. Pressure limitations for Parker compounds are shown on page 2 and are based on our recommended dimensions and tolerances.

FLUID COMPATIBILITY is the final requirement for material selection. As all elastomers are affected to some degree by their fluid environment, it is vital that a material be selected that will be affected the LEAST by the fluid and again, there is the factor of TIME to be considered, a material which may be fine for 100 hours @ 200°F in the specified fluid may soften just enough @ 400 hours to extrude during a high pressure excursion. For your information, a short fluid compatibility table is provided on the next page.


TESTING of all sealing materials is recommended as there are many factors which may effect seal life. Parker suggests that all new and replacement materials and seal geometries be fully evaluated under actual service conditions before production and / or major retrofit programs are finalized.

NITROXILE

ALL ABOVE -

ETHYLENE PROPYLENE

FLUOROCARBON



DYNOTHANE MOLYTHANE ULTRATHANE POLYMITE FLUOROMYTE NITRILE NITRILE NITRILE NITRILE OR EPR FLUOROCARBON

PARKER PolyPak MATERIAL COMBINATIONS

-Parker

NITRILE

ETHYLENE PROPYLENE

FLUOROCARBON

METAL O-SPRING



FLUID COMPATIBILITY TABLE

This table is a brief guide to some of the more common hydraulic, pneumatic and general service fluids. For more detailed information on these fluids or other not listed, contact US.

Chemical/Fluid Media

GENERAL FLUIDS

Air and Dry Gas

Acid, weak<50% conc.
Alcohols
Brake Fluids
Chlorine, dry
Fthers

Gasoline

Glycols, ethylene base Hydrogen

Hydroxydes, weak < 50% conc. Jet Fuel, JP-4, JP-5, JP-6

Oil, Mil-H-5606, R-3065, Std. 417, Petroleum Base

Oli, minaral base Water, hot 180oF

Water, cold under 150oF

WATER-GLYCOL FLUIDS

Fyre-Safe 160,225				- 1						
Fyreguard 150, 200, G-200										
Houghto-Safe 500, 600										
Hydrolube 150LT, 200LT, 275LT, 300LT										
0 : ()!!!(0.15)!!!(0.00)!!!(0.00										

E4183A80 ETHYLENE PROPYLENE

N4115A75 NITRILE N4180A80 NITRILE N4181A85 NITRILE N4182A75 NITRILE E4207A90 ETHYLENE PROPYLENE E4270A90 ETHYLENE PROPYLENE

V4208A90 FLUOROCARBON V4266A95 FLUOROCARBON N4274A85 NITROXYLE (ELF) N4263A90 NITROXYLE

N4257A80 NITROXYLE

P4611A90 PARKERTHANE

P4615A90 MOLYTHANE

P4622A90 ULTRATHANE P4617D65 MOLYTHANE

P4693A90 DYNOTHANE

V4205A75 FLUOROCARBON

Santosafe W/G15, W/G20, W/G30 WATER IN OIL FMIII SION FLUIDS

MAIEU-IN-OIL EMOLSION LEOI
Fyre-Safe 500
Gulf ER Fluid

Houghto-Safe 5000 Hulsafe 500,600

Inverse Emulsion

Invert Emulsion

AIRCRAFT TYPE FLUIDS

Aerosate 2300, ER			- 1						1 1		
Phosphate Ester Hydraulic Fluid											
Skydrol 500B, 500B4, 500C											
Hyjet W III IVA											

INDUSTRIAL PHOSPHATE ESTER FLUIDS

Fyrquel Blend G, Pydraul 10E										
Chevron FR-32, FR-46, FR-66, FR-150										
Fyrquel 90, 150, 220, 300, 550, 550RC, 1000, 149ELT, 140RO, 220RO, G l										
Houghto-Safe 1000, 1010, 1055, 1120										
P-37, P-40, P-43, P-45, P-47										
PE-15, PE-22, PE-30, PE-55										
Phosphate Ester Hyd. Fluid										
Pydraul 29E-LT, 30-E, 50-E, 65-E, 90E, 115E										

PHOSPHATE ESTER-OIL BLENDS

Phosphate Ester, Base Fluid										
Pydraul 230-C, 312-C, 540-C, MC										
Sunguard 350 Safety Fluid										
Vital Hydraulic Fluid										

1. - Generally Aceptable.

□-Check specific fluid with us

2. - Consult page C-5 for temperature ratings.

3. - Recommendations should be tested in service before production.

www.sealsonline.com



Vanier (QC) Tel.: (418) 688-3202 Fax.: (418) 688-4272 Tel.: (514) 334-2220 Fax.: (514) 333-8329 St-Laurent (QC) Mississauga (ON) Tel.: (905) 238-5885 Fax.: (905) 281-0763

Solution of

PolyPak ROD DESIGN TABLE

CROSS-SECTION TYPE B POLYPAK

Rod Seal Example

Given desired rod diameter of 2-1/2" with a normal seal cross-section of 1/4".

Rod dia.(N) = 2.500 + .000/-.002

Throat dia.(P) = Nmax + .001 + .003/-.000 = 2.500 + .001 = 2.501 + .003/-.000

Groove dia.(D) = Nmax + 2(I) + .003/-.000 = 2.500 + 2(.250) = 2.750 + .003/-.000

Axial groove length(E) = Given .413 + .013/-.000

N			E		Р	D
Nominal Rod I.D. Range	Nominal Radial Cross-Section		Axial Groo Standard	ve Length Deep & Type B	Throat Diameter	Groove O.D.
1/4" - 2 1/8" ± .000	1/8	125	138 ± 015	$.275 \pm .015_{.000}$	Nmax + .001 $\pm \frac{.002}{.000}$	Nmax + 2 (I) ± .002
5/16" - 4 1/4" ± .000	3/16	.187	$206 \pm \frac{015}{000}$	$^{.343}_{.413} \pm ^{.015}_{.000}$	Nmax + .001 $\pm \frac{.002}{.000}$	Nmax + 2 (I) ± .002
1/4" - 12 3/4" ± .000	1/4	.250	$275 \pm {015 \atop 000}$	413 ± .015 .618 ± .000	Nmax + .001 $\pm \frac{.003}{.000}$	Nmax + 2 (I) $\pm \frac{.003}{.000}$
3/4" - 9 5/8" ± .000	5/16	.312	$343 \pm {015 \atop 000}$.550 .688 ± .000	Nmax + .002 $\pm \frac{.003}{.000}$	Nmax + 2 (I) $\pm \frac{.004}{.000}$
1 1/2" - 14 3/4" ± .000	3/8	.375	412 ± .015	.550 .688 ± .000	Nmax + .002 $\pm \frac{.004}{.000}$	Nmax + 2 (I) $\pm \frac{.005}{.000}$
2 1/4" - 5" ± .000	7/16	.437	.481 ± .015	688 ± 015	Nmax + .002 $\pm \frac{.004}{.000}$	Nmax + 2 (I) $\pm \frac{.006}{.000}$
1 3/4" - 24 7/8" ± .000	1/2	.500	$550 \pm {015 \atop 000}$.825 ± .015	Nmax + .002 $\pm \frac{.005}{.000}$	Nmax + 2 (I) $\pm \frac{.007}{.000}$
2 3/4" - 19 3/4" ± .000	5/8	.625	$688 \pm \frac{.015}{.000}$	$\frac{1.100}{1.375} \pm \frac{.015}{.000}$	Nmax + .003 $\pm \frac{.006}{.000}$	Nmax + 2 (I) $\pm \frac{.009}{.000}$
7 1/4" - 31" ± .000	3/4	.750	$825 \pm \frac{.015}{.000}$	1.238 1.375 ± .000	Nmax + .003 $\pm \frac{.007}{.000}$	Nmax + 2 (I) $\pm \frac{.011}{.000}$
15" - 39" ± .000	1	1.000	1.100 ± .015	$1.650 \pm .015_{.000}$	Nmax + .004 $\pm \frac{.009}{.000}$	Nmax + 2 (I) $\pm \frac{.015}{.000}$
F1	F2			F3	F4	F5

Notes:

Note:



















F₁ - The Nominal Rod Diameter spread shown is taken from Price List PPD3701. Available sizes fall in cross-section range. Rod size range given based on Type B Poly Pak availability.

F₂ – The Radial Cross-Section I is shown as a fraction for Seal Reference and a three place decimal for Gland Reference.

 F_3^2 – There may be two possible Axial Groove Lengths for some cross-sections.

 F_4° – The throat diameters are simply figured by taking the maximum Rod Diameter plus the noted clearance.


 F_s^4 – The Groove Outside Diameter is calculated by taking the maximum Rod Diameter plus two radial cross-sections I.

^{1 –} Molythane parts can be stretched up to 5% of its diameter or compressed up to 2% for rod applications. Therefore if odd size rods or bores are encountered, existing sizes can be used without special non-available seals. Careful attention must be taken when using the 5% rule so that the radial cross-section "I" must be maintained no matter what dimension the rod or piston actually measures. Careful attention must be taken to select a size that requires 5% max **stretch** on the diameter in piston applications, and 2% max. **compression** on the diameter in rod applications.

^{2 –} Axial groove lengths for PolyPaks with non-positively actuated modular back-ups are calculated by: (nominal radial c/s desired x 1.100) + "E".



PolyPak PISTON DESIGN TABLE



Piston Seal Example

Given desired bore diameter of 6" with a normal seal cross-section of 3/8".

Bore dia.(J) = 6.000 + .004/-.000

Piston $0.D.(G) = J_{min} - .002 + .000/-.002 = 6.000 - .002 = 5.998 + .000/-.002$

Groove I.D.(H) = J_{min} - 2(I) +.000/-.005 = 6.000 - 2(.375) = 5.250 +.000/-.005

Axial groove length(E) = Given .550 + .015/-.000

Nominal Bore	Nominal Radial		Axial Gro	E ove Length	G Piston O.D.	H Groove I.D.
0.D. Range 5/16" - 6" ± .002	Cross-Section 1/8	.125	Standard .138 ± .000	Deep .275 ± .015	Formula Jmin + .001 ± .000	Formula Jmin + 2 (I) ± .000 .002
9/16" - 6 11/16" ± .002	3/16	.187	206 ± 015	$^{343}_{413} \pm ^{015}_{000}$	Jmin + .001 ± .000	Jmin + 2 (I) ± .000
3/4" - 14" ± .003	1/4	.250	.275 ± .015	.413 ± .015 .618 ± .000	Jmin + .001 ± .000	Jmin + 2 (I) ± .000
1" - 15 1/2" ± .003	5/16	.312	$343 \pm {015 \atop 000}$.550 .688 ± .000	Jmin + .002 ± .000	$Jmin + 2 (I) \pm \frac{.000}{.004}$
1 1/4" - 20 1/4" ± .000	3/8	.375	412 ± 000	.550 ± .015 .688 ± .000	Jmin + .002 ± .000	Jmin + 2 (I) ± .000
1 7/8" - 6 3/8" ± .005	7/16	.437	$481 \pm {015 \atop 000}$.688 .825 ± .000	Jmin + .002 ± .000	Jmin + 2 (I) ± .000
1 5/8" - 52 1/2" ± .005	1/2	.500	$550 \pm {015 \atop 000}$.688 ± .015 .825 [±] .000	Jmin + .002 ± .000	Jmin + 2 (I) ± .000
3 5/8" - 5 1/2" ± .006	9/16	.562	$618 \pm \frac{.015}{.000}$	$.963 \pm .015_{.000}$	Jmin + .002 ± .000	$Jmin + 2 (I) \pm \frac{.000}{.008}$
2 1/2" - 26" ± .006	5/8	.625	$688 \pm {015 \atop 000}$	1.100 ± .015 1.375 ± .000	Jmin + .003 ± .000	Jmin + 2 (I) ± .000
4 1/2" - 27 1/2" ± .007	3/4	.750	$825 \pm {015 \atop 000}$	$\begin{array}{c} 1.238 \\ 1.375 \end{array} \pm \begin{array}{c} 015 \\ 000 \end{array}$	Jmin + .003 ± .000	Jmin + 2 (I) ± .000
6" - 21 3/4" ± .008	7/8	.875	$963 \pm {015 \atop 000}$	$\frac{1.375}{1.513} \pm \frac{.015}{.000}$	Jmin + .004 ± .000	Jmin + 2 (I) ± .000
4" - 18" ± .009	1	1.000	$1.100 \pm .015_{.000}$	$1.650 \pm \frac{.015}{.000}$	Jmin + .004 ± .000	Jmin + 2 (I) ± .000
F1	F2			F3	F4	F5

Notes

- F₁ The Nominal Bore Diameter spread shown is taken from Parker availability tooling list.
- F₂ The Radial Cross-Section I is shown as a fraction for Seal Reference and a three place decimal for Gland Reference.
- F_3^- There may be two possible Axial Groove Lengths for some cross-sections.
- F_4^2 The Piston outside Diameter is simply figured by taking the minimum Bore Diameter minus the noted clearance.
- $F_{\rm s}$ The Groove Inside Diameter is calculated by taking the minimum Bore Diameter minus two radial cross-sections I.

Note

- 1 Molythane parts can be stretched up to 5% of its diameter or compressed up to 2% for rod applications. Therefore if odd size rods or bores are encountered, existing sizes can be used without special non-available seals. Careful attention must be taken when using the 5% rule so that the radial cross-section "I" must be maintained no matter what dimension the rod or piston actually measures. Careful attention must be taken to select a size that requires 5% max stretch on the diameter in piston applications, and 2% max. compression on the diameter in rod applications.
- 2 Axial groove lengths for Poly Paks with non-positively actuated modular back-ups are calculated by: (nominal radial c/s desired x 1.100) + "E".



www.sealsonline.com



8

 Vanier (QC)
 Tel.: (418) 688-3202
 Fax.: (418) 688-4272

 St-Laurent (QC)
 Tel.: (514) 334-2220
 Fax.: (514) 333-8329

 Mississauga (ON)
 Tel.: (905) 238-5885
 Fax.: (905) 281-0763